

Scheda tecnica

Ossido di magnesio

Magnesite caustica calcinata

		Specification	Typical
MgO	: (min)	83.00%	
MgO Loss Free	: "	84.00%	
SiO ₂	: (max)	12.00%	9.50%
CaO	: "	3.20%	2.80%
Fe ₂ O ₃	: "	0.40%	0.30%
Al ₂ O ₃	: "	0.30%	0.15%
SO ₃	: "	0.30%	0.12%
L.O.I.	:		1.00-2.00%

Method: By X-RF analysis

Granulometria

97% sotto i 100 micron

imballo

sacchi da 25 kg

Esmar srl

Via Emilia Romagna, 82 41049 Sassuolo (MO)- Italia - Tel. 0536-800133 / 804617 Fax 0536-802482
Capitale sociale Eur 10.000,00 i.v. C.F. e P.I. 03439320361 REA MO 387795 email: info@esmar.it